



Vogt Valves
*The Connection Bulletin for
Sour Service Valve Applications*

CB 17

Sour Service Valve Applications



WHAT IS A "SOOR ENVIRONMENT"?

Fluids, notably petroleum crudes and gases, containing water (H₂O) as a liquid and hydrogen sulfide (H₂S) are considered to be "sour environments." Piping and components transporting these fluids are considered to be in sour service.

WHAT'S NEW?

The "Sour Environment" problem has existed for decades but became a major concern in the 1970's with the increased production of H₂S bearing hydrocarbon crudes and gases which caused a noticeable increase in failures of materials.

WHAT'S THE PROBLEM?

Valves operating in a sour environment have prematurely failed as a result of a corrosion process known as **sulfide stress cracking** (SSC). SSC is a **hydrogen embrittlement** phenomenon that occurs in high strength steels and in the heat-affected zones (HAZ) of steel weldments. It occurs as an unexpected brittle failure in materials when subjected to stresses that are even less than their yield strength.

WHAT MATERIALS ARE AFFECTED?

Most alloys and particularly ferrous metals, whether hardened by heat treatment or cold work to hardnesses above Rc-22, are susceptible to SSC. Heat-affected zones (HAZ) in welds with hardnesses above Rc-22 are also susceptible.

THE CONNECTION for SOOR SERVICE VALVE APPLICATIONS

WHAT'S NACE?

National Association of Corrosion Engineers. This highly respected organization has recognized the problem and issued Standard MR-01-75 and Revisions, "SULFIDE STRESS CRACKING RESISTANT METALLIC MATERIAL FOR OIL FIELD EQUIPMENT."

Sour Service Valve Applications

WHAT'S MR-01-75 ABOUT?

MR-01-75 is a material standard—not a design standard. It is an aid in the selection of materials for those “Sour Environment” applications with conditions present which could result in SSC. The standard discusses the sour environment and presents guidelines in the H₂S concentration and pressure relationships where SSC can occur in sour gas and sour multi-phase systems. The standard has an excellent listing of ferrous and non-ferrous materials that are resistant to SSC. Copies of MR-01-75, including revisions, can be obtained by writing:
 NACE INTERNATIONAL,
 P.O. Box 218340,
 Houston, Texas 77218.

ANY OTHER CONSIDERATIONS?

Yes. In addition to H₂S, carbon dioxide (CO₂) and water containing chlorides may also be present in crude oils and gases. This environment can lead to **degradation** of exposed material by **weight loss corrosion** (pitting, crevice and general corrosion) and other forms of **environmental embrittlement**.

MR-01-75 covers only **materials** resistant to SSC but other considerations must be recognized and properly dealt with to assure efficient and safe control of hazardous media.

DOES VOGT MEET THE CHALLENGE?

Yes. We offer a number of valve series that are manufactured under a **controlled manufacturing** system that assures all materials, welds, and fabrication processes meet MR-01-75 and can be certified on request.

All Vogt forged steel valve bodies and bonnets meet NACE MR-01-75. However, we exert extreme care to control the manufacturing process for valve trim parts, bolting, and pressure boundary welds to maintain appropriate chemistry and mechanical properties which are resistant to SSC.

WHAT'S THE BEST BOLTING?

Vogt ASTM A105 NACE valves use ASTM A193 Gr. B7M or B8M CL1 material for exposed and non-exposed bonnet bolt applications. For temperature to -50°F, Vogt ASTM A350, Gr. LF2 valves use ASTM A320, Gr. L7M or B8M CL1 bonnet bolts for exposed and non-exposed bolt applications.

NACE MR-01-75 addresses bolting requirements in two categories:

1. **Exposed Bolting:**

Bolting which in service is exposed directly to the sour environment or which will be buried, insulated or equipped with flange protectors or otherwise denied direct exposure to the open atmosphere.

2. **Non Exposed Bolting:**

Bolting which is exposed to the open atmosphere rather than the sour environment.

WHAT'S THE “BEST” TRIM?

No single trim is “Best” for all sour environment applications, particularly when H₂S, CO₂, and water containing chlorides are present.

Vogt makes maximum use of 13% Cr., 316 stainless steel and Monel trim packages which offer superior corrosion resistance when matched to the sour environment and considering CO₂ and water containing chlorides.

After your careful analysis of the “Sour Environment” conditions, the selection of trim materials may be made from the following “trim suggestions” chart.

Sour Service Valve Applications

TRIM SUGGESTIONS FOR APPLICATIONS WITHIN THE SSC REGION[▲]

Service	Also Present	Temperature Range	Vogt Suggested Trim
Oil/Gas	H ₂ S and H ₂ O	-20°F to 800°F	316 or 13 Cr.
Oil/Gas	H ₂ S, H ₂ O, CO ₂	-20°F to 800°F	316, 13 Cr. or <i>Monel</i> *
Oil/Gas	H ₂ S, H ₂ O and Chlorides	-20°F to 800°F	<i>Monel</i> * or 13 Cr.
Oil/Gas	H ₂ S, H ₂ O, CO ₂ and Chlorides	-20°F to 800°F	<i>Monel</i> * or 13 Cr.

[▲] See Figures No. 1 and No. 2, NACE MR-01-75.

* In multiphase systems significant general corrosion may occur at temperatures above 300°F when CO₂, H₂S and chlorides are present.

For sour service valve applications outside the scope of NACE Standard MR-01-75 SSC region requirements, Vogt suggests that our standard carbon steel valves containing 13 Cr., Type 316 stainless steel trim (F8M) or *Monel* (mm) trim be used.

TRIM SUFFIX DESIGNATIONS are used with series numbers to indicate the special characteristics of a valve for sour service applications.

Suffix for NACE Trim Designation	Special Characteristics
MBS (Monel)	<i>Monel</i> Trim <i>Monel</i> /Flexible Graphite Spiral Wound Gasket Flexible Graphite Packing B7M Bonnet Bolting Full Rating
MB8 (316SS)	Solution Annealed 316 Trim 316/Flexible Graphite Spiral Wound Gasket Flexible Graphite Packing B8MCL1 Bonnet Bolting Hard Faced Seats and Gate (or Disc) Full Rating
MB6 (13 Cr.)	Soft 13 Cr. Trim 304/Flexible Graphite Spiral Wound Gasket Flexible Graphite Packing B7M Bonnet bolting Hard Faced Seats and Gate (or Disc) Full Rating

Sour Service Valve Applications

TYPICAL VOGT VALVES MEETING MATERIAL REQUIREMENTS OF NACE STANDARD MR-01-75

A number of outside screw and yoke (OS&Y) and inside screw (ISS) valves utilizing materials selected from NACE MR-01-75 are offered. These valves are carried in stock and are available with written certification to NACE Standard MR-01-75 when specified. For a more complete list of Vogt valves meeting NACE MR-01-75, see Vogt V V200 Catalog.

Order by size and number

Description	Pressure/Size Designation	Material		Series Number	
		Body/Bonnet	Trim	Threaded	Socket Weld
Globe Valves Bolted Bonnet OS&Y	Class 800 1975 psi@ 100°F Sizes 1/2 - 2	A105	316M Trim★ B8MCL1 Bolting	12141MB8	SW 12141MB8
Gate Valves Bolted Bonnet OS&Y	Class 800 1975 psi@ 100°F Sizes 1/2 - 2 (to -50°F)	A350, Gr. LF2	316M Trim★ B8MCL1 Bolting	32111MB8	SW 32111MB8
Gate Valves Bolted Bonnet OS&Y	Class 800 1975 psi@100°F Sizes 1/4 - 2	A105	316M Trim★ B8MCL1 Bolting	12111MB8	SW 12111MB8
		A105	Monel Trim B7M Bolting	12111MBS	SW 12111MBS
		A105	Soft 13 Cr. Trim B7M Bolting	12111MB6	SW 12111MB6
Gate Valves Welded Bonnet OS&Y	Class 800 1975 psi@ 100°F Sizes 1/4 - 2	A105	Monel	2801MBS	SW 2801MBS
		A105	316★	2801MB8	SW 2801MB8
Gate Valves Union Bonnet ISS	Class 800 1975 psi@ 100°F Sizes 1/4 - 2	A105	Monel	59851MBS	SW 59851MBS
Gate Valves Bolted Bonnet OS&Y	Class 1500 3705 psi@ 100°F Sizes 1/2 - 2 (to -50°F)	A350, Gr. LF2	316M Trim★ B8MCL1 Bolting	35111MB8	SW 35111MB8
Gate Valves Welded Bonnet OS&Y	Class 1500 3705 psi@ 100°F Sizes 1/2 - 2	A105	316M Trim★ B8MCL1 Bolting	15111MB8	SW 15111MB8
		A105	Monel Trim B7M Bolting	15111MBS	SW 15111MBS
		A105	Soft 13 Cr. Trim B7M Bolting	15111MB6	SW 15111MB6
Gate Valves Welded Bonnet OS&Y	Class 1500 3705 psi@ 100°F Sizes 1/2 - 2	A105	Monel	15801MBS	SW 15801MBS
		A105	316M Trim★ B8MCL1 Bolting	15801MB8	SW 15801MB8

GLOBE ★ Discs and integral seats are hard faced. The trim is solution annealed after machining to assure Rc-22 Max. hardness.

GATE ★ Seats and wedge are hard faced and trim parts solution annealed after machining to assure Rc-22 Max. hardness.

Most Vogt valve designs can be furnished in accordance with NACE MR-01-75 including **special design requirements**.

NOTE: All forged steel fittings shown in our current catalogs meet the requirements of NACE MR-01-75 and are available for immediate shipment from our warehouse or Vogt distributors' stock.



Vogt Valves

1511 Jefferson Street
Sulphur Springs, TX 75482

US Sales Offices

Phone: 903-885-3151
Fax: 903-439-3386

Toll-Free Telephone Service

1-800-225-6989

Visit Our Website

www.flowserve.com

After Hours Customer Service

1-800-543-3927

Flowserve Corporation has established industry leadership in the design and manufacture of its products. When properly selected, this Flowserve product is designed to perform its intended function safely during its useful life. However, the purchaser or user of Flowserve products should be aware that Flowserve products might be used in numerous applications under a wide variety of industrial service conditions. Although Flowserve can (and often does) provide general guidelines, it cannot provide specific data and warnings for all possible applications. The purchaser/user must therefore assume the ultimate responsibility for the proper sizing and selection, installation, operation, and maintenance of Flowserve products. The purchaser/user should read and understand the Installation Operation Maintenance (IOM) instructions included with the product, and train its employees and contractors in the safe use of Flowserve products in connection with the specific application.

While the information and specifications contained in this literature are believed to be accurate, they are supplied for informative purposes only and should not be considered certified or as a guarantee of satisfactory results by reliance thereon. Nothing contained herein is to be construed as a warranty or guarantee, express or implied, regarding any matter with respect to this product. Because Flowserve is continually improving and upgrading its product design, the specifications, dimensions and information contained herein are subject to change without notice. Should any question arise concerning these provisions, the purchaser/user should contact Flowserve Corporation at any one of its worldwide operations or offices.

For more information about Flowserve Corporation, contact www.flowserve.com or call USA 1-800-225-6989.

FLOWSERVE CORPORATION

FLOW CONTROL DIVISION

Vogt Valves

1511 Jefferson Street
Sulphur Springs, TX 75482
Phone: 903-885-3151
Facsimile: 903-439-3386